

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number
WO 2005/065911 A1

(51) International Patent Classification⁷: **B29C 43/00**,
A61L 27/16, C08L 23/06 // A61L 27/14

(21) International Application Number:
PCT/NL2005/000005

(22) International Filing Date: 7 January 2005 (07.01.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
1025176 7 January 2004 (07.01.2004) NL

(71) Applicant (for all designated States except US): **DSM IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MARISSEN, Roelof** [NL/NL]; Koningstraat 55, NL-6121 HS Born (NL). **SMIT, Leo** [NL/NL]; Douvenderweg 15, NL-6438 AE Oirsbeek (NL). **SNIJDER, Carina, Sacha** [NL/NL]; Vogezenstraat 18, NL-6137 JR Sittard (NL).

(74) Agent: **BOOTSMA, J., P., C.**; DSM Intellectual Property, P.O. Box 9, NL-6160 MA Geleen (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR MANUFACTURING A PROSTHETIC JOINT



(57) Abstract: The application relates to a process for manufacturing a prosthetic joint with at least one loaded surface which consists at least partially of polyethylene, comprising compressing one or more layers of a woven fabric of drawn gel-spun polyethylene fibres into the desired shape in a hollow mould part using a plug at a pressure of at least 0.05 MPa and at a temperature of between 120 and 165°C and below the crystalline melting point of the polyethylene at the prevailing temperature and pressure, without a matrix material being present, and at least the woven fabric in a layer situated on a loaded surface comprising at least 90wt % of fibres with a titre of at most 1000 denier, and to a prosthetic joint with a crease-free surface.

WO 2005/065911 A1